

CUSTOMCRETE[®] LATEX MORTAR ADMIX

- High strength additive
- Mix with CreteMix™ Mortar or a site-mixed blend
- Adds shock resistance and flexibility
- Excellent for exterior use and underwater installations

PRODUCT DESCRIPTION

CustomCrete[®] Latex Mortar Admix is formulated to be used with CreteMix™ Mortar to form a high strength thin-bed mortar or as an additive to a site-mixed sand/cement blend. Adds flexibility and shock resistance for use in heavy traffic conditions in industrial, commercial and institutional installations. Frost resistant, it's excellent for exterior use in cold climates. Also for use in wet areas and underwater installations such as pools and fountains.

USES

Use as an additive when mixing CreteMix Mortar or to a site-mixed sand/cement blend. Refer to the CreteMix Mortar directions for appropriate areas of use and tile types.

MIXING

Thoroughly mix a 50 lb. (22.68 kg) bag of CreteMix Mortar with 5 quarts (4.73 L) CustomCrete Latex Mortar Admix to a smooth, paste-like consistency. Mix by hand or use a low speed (150-200 RPM) 1/2" (13 mm) drill. Let slake or stand 5 - 10 minutes, stir again and use. Stir occasionally to keep fluffy, but do not retemper (add more additive). When properly mixed, troweled ridges will stand with little or no slump. For a sand/cement site mix, dry blend one 94 lb. (42.68 kg) bag of Portland cement with one 100 lb. (45.36 kg) bag of #60 silica sand and mix with 5 gallons (7.56 L) of CustomCrete.

APPLICATION

Refer to the CreteMix Mortar directions for proper surface preparation and application instructions.

CURING

Allow to cure for a minimum of 24 hours before grouting or light traffic, depending upon temperature and humidity. In areas that will be continually wet (e.g. swimming pools, fountains), it's recommended that the completed installation be cured a minimum of 14 days and allowed to thoroughly dry before water submersion. Curing times vary with weather conditions and humidity; special conditions may require curing up to 28 days.

COVERAGE

When mixed with CreteMix Mortar: 80 - 100 sq. ft. per 50 lbs. (7.4 - 9.3 m²/22.68 kg) applied with a 1/4" x 1/4" x 1/4" (6 x 6 x 6 mm) square-notch trowel.

CLEAN-UP

Clean with soap and water before material dries. Cured material is difficult to clean from surfaces.

SAFETY

Do not take internally. Avoid eye and skin contact. If eye contact occurs, immediately flush with water for 15 minutes and consult a physician.

STORAGE

Keep from freezing. Close container after each use.

ORDERING INFORMATION

ITEM CODE	SIZE	COLOR	PACKAGE
CCR5	5 gallon (18.93 L)	White	Pail
CCR55	55 gallon (208.19 L)	White	Drum

TECHNICAL DATA

Exceeds ANSI A118.4 specifications.

	CRETEMIX MORTAR WITH CUSTOMCRETE
Open Time	50 minutes
Adjustment Time	30 minutes
Shear Bond @ 28 Days:	
Bisque Tile	500 psi (35.2 kg/cm ²)
Porcelain Tile	500 psi (35.2 kg/cm ²)



CUSTOM[®]
BUILDING PRODUCTS

Seal Beach, CA (562) 598-8808 Customer Support (800) 272-8786

www.custombuildingproducts.com Manufacturing facilities nationwide.